



International Products CORPORATION

201 Connecticut Drive | Burlington, NJ 08016 | USA
609-386-8770 | Fax: 609-386-8438 | www.ipcol.com

Metal Compatibility of Aqueous Cleaners at 2%

% Change in Mass of Selected Metals After Immersion in 2% Cleaning Solutions

Metal	Immersion Time	MICRO-90®		LF2100®		MICRO® A07		SURFACE-CLEANSE/930®		ZYMIT® Low-foam		ZYMIT® Pro		Water (Control)	
		25° C	40° C	25° C	40° C	25° C	40° C	25° C	40° C	25° C	40° C	25° C	40° C	25° C	40° C
Aluminum	24 Hours	-0.5%	-0.3%	-0.1%	-0.5%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	-0.1%
	288 Hours	-0.3%	-0.2%	-0.2%	-0.5%	0.0%	-0.2%	0.0%	0.0%	0.0%	0.0%	-0.1%	-0.3%	0.0%	0.0%
Brass Alloy	24 Hours	-0.1%	-0.1%	-0.1%	-0.1%	0.0%	-0.1%	0.0%	0.0%	0.0%	0.0%	0.0%	-0.1%	0.0%	-0.1%
	288 Hours	-0.2%	-0.3%	-0.2%	-0.2%	-0.4%	-1.0%	0.0%	0.0%	-0.1%	-0.5%	-0.2%	-0.4%	0.0%	0.0%
Bronze Alloy 220	24 Hours	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	-0.2%	-0.3%	-0.1%	-0.1%	-0.5%	+0.1%	0.0%	0.0%	-0.1%	-0.2%	-0.1%	-0.2%	0.0%	0.0%
Cold Rolled Steel	24 Hours	0.0%	-0.2%	-0.1%	0.0%	-0.3%	-0.7%	-0.1%	-0.1%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	-1.3%	-2.3%	-0.1%	-0.2%	-2.0%	-2.7%	-1.2%	-1.0%	-0.1%	-0.2%	-0.1%	-0.1%	-0.2%	-0.2%
Copper Alloy CA 110	24 Hours	0.0%	-0.1%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	-0.1%	-0.3%	-0.1%	-0.3%	-0.5%	0.0%	0.0%	0.0%	-0.1%	-0.3%	-0.1%	-0.2%	0.0%	0.0%
Monel 400	24 Hours	0.0%	-0.1%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	-0.1%	-0.2%	0.0%	0.0%	-0.3%	-1.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
Stainless Steel	24 Hours	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
Titanium Alloy, 8% Mn	24 Hours	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%
	288 Hours	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%	0.0%

Test Method: ASTM D543-95

The recommended concentration use for the above cleaners is 1.0% to 2.0%. Test data is provided for comparison purposes only. Individuals should conduct their own tests for compatibility verification. Please contact International Products Corporation for compatibility information on any metal not shown.

For Sales and Service in Europe:

Unit 5, Green Lane Business Park | 238 Green Lane | London SE9 3TL | U.K.
Tel: 020-8857-5678 | Fax: 020-8857-1313 | www.ipcol.com